



# J-Line™ Jacketed Tubing

Industry standard tubing with an extruded SV47 jacket is used in applications where additional corrosion protection or mechanical protection is required. J-Line is not insulated or heated.



J-Line tubing is ideal for pneumatic and hydraulic applications in corrosive atmospheres. Industry standard tubing coated with O'Brien SV47 polymer provides increased protection against galvanic and atmospheric corrosion as well as cushioning the tube against wear from vibration.

#### Uses:

Instrument air  
Pneumatic process control lines  
Municipal water wells  
Down-hole chemical injection  
Chemical injection  
Seal water feed lines  
Direct burial  
Windblown sand

#### Availability:

J-Line is available in prepackaged cut-to-length sections and long continuous bulk coil either directly from O'Brien or through your local distributor. Standard materials are copper and welded or seamless 316/316L stainless steel.

#### Installation:

Install J-Line as you would ordinary tubing except the SV47 protective jacket is removed to accommodate standard compression fittings.

#### Available materials and sizes:

(consult factory for other sizes and materials)

#### Copper

Grade - C12200

ASTM - B-68, B-75

**J2** 1/4" OD x 0.030 wall

**C3** 3/8" OD x 0.032 wall

**D4** 1/2" OD x 0.035 wall

**MD6** 6mm OD x 1mm wall

**MD8** 8mm OD x 1mm wall

**MD12** 12mm OD x 1mm wall

#### Stainless Steel

Grade - 316/316L

ASTM - A-269, A-450 & A-213 EAW (Seamless Only)

Metric tube also meets - DIN 17458 1.4401/1.4404

#### Welded

**A2** 1/4" OD x 0.035 wall

**A3** 3/8" OD x 0.035 wall

**A4** 1/2" OD x 0.035 wall

#### Seamless

**F2** 1/4" OD x 0.035 wall

**F3** 3/8" OD x 0.035 wall

**F4** 1/2" OD x 0.035 wall

**B4** 1/2" OD x 0.049 wall

**MF6** 6mm OD x 1mm wall

**MF8** 8mm OD x 1mm wall

**MF12** 12mm OD x 1mm wall

**MB12** 12mm OD x 1.5mm wall

# J-Line Jacketed Tubing



## SV47 Jacket

SV47 is a proprietary thermoplastic formulation that exceeds the requirements of 105C PVC and outperforms other PVC jacket materials in UV resistance as well as providing low temperature flexibility to  $-30^{\circ}\text{F}/-35^{\circ}\text{C}$ .

	Standard 105C PVC	O'Brien SV47
Abrasion Resistance	G	G
Tensile Strength PSI	18-1900	2200
Elongation %	250	350
Hardness, Shore A	85-90	80
Minimum Installation Temperature	15°F/-9°C	-30°F/-35°C
UL94 Flame	V2	V2
Halogenated (Chlorides)	YES	YES
Maximum Service Temperature	220°F/ 105°C	220°F/ 105°C
Water Absorption %	0.1%	0.1%
Aromatic Hydrocarbons	F	F
Weathering	G	G
UV Resistance	F	G

Specifications subject to change without notice.



Offices:  
 USA · 1900 Crystal Industrial Ct. · St. Louis, MO 63114 · USA · Ph (+1) 314/236-2020 · Fax (+1) 314/236-2080  
 BELGIUM · Mallekotstraat 65 · B2500 Lier Belgium · Ph (+32) 3 491 9875 · Fax (+32) 3 491 9876  
 obcorp@obcorp.com · www.obrien-analytical.com · www.obcorp.com